



269 FAST DRY URETHANE

JULY 2015

2K Acrylic Polyurethane

Product Data

A two pack polyurethane, based on acrylic resin and N/C.

- Very fast drying (comparable to lacquers)
- Excellent wet and dry heat resistance
- Very good mar resistance
- Excellent chemical / solvent resistance
- Excellent abrasion resistance
- Available in various gloss levels (10%, 30%, 50%, full gloss).

Uses

269A Fast Dry Urethane is a high quality finish for furniture, toys, shop fittings, doors, cabinets, desks, panelling, partitions and most interior woodwork.

Ideal for use in bathroom and kitchen areas. NOT for external use.

Colour Availability

Clear and tinted colours @ POS.

Packaging

269A – 1L, 4L, 20L

269B – 250ml, 1L

Substrate & Surface Preparation

Wood – sand and dust down. Prime

MDF – sand faces with 150 grit, edges with 120 grit followed by 180 grit in the opposite direction. Prime.

Original Finish – sand and dust down. Degrease.

Total Solids Content

40.4% (wt), 27.1% (vol) – (White – catalysed)

Mixing Ratio

Mix 8L 269A with 1L 269B Hardener

Thinning and Clean Up

Once catalysed, thin as follows:

Normal / Warm Conditions: Add 50-75% 684 or 140.

Warm / Humid Conditions: Add 75% of a 9:1 blend of 140 Reducer:539R Acrylic Retarder.

269 Fast Dry Urethane must be thinned correctly to achieve best results.

Clean gun and equipment with 140 Reducer or 684 Reducer.

Application

Spray – conventional.

This product should be layered up at approximately 50 microns WFT per application until required WFT is achieved.

Best results are obtained over a 2 pack polyurethane primer / sealer. Do NOT use over N/C primer / sealer.

Drying

Dust free: 5 mins

Touch dry: 10 mins

Dry to tape: 1 hour

Hard dry: 16-24 hours

Recoat time: Wet on wet – under 2 hours, or after 24 hours – with sanding.

Theoretical Coverage

Approximately 4.5 sq. m/litre @ 60µm DFT (White).

Practical coverage rates will be lower than theoretical and this must be taken into consideration when calculating costs.

Safety Precautions

Read each component's material safety data sheet before use. Mixed material has hazards of each component. Safety precautions must be strictly followed during storage, handling and use.

Health & Safety

Avoid breathing vapour. Use with adequate ventilation. High concentrations of vapour may cause headache or nausea, affect the nervous system and respiration.

Do not use in the presence of naked flame or other sources of ignition. Store away from heat.

Wear safety glasses/goggles, an air supplied respirator or hood and PVC or nitrile chemical handling gloves.

If spraying in a confined area, a positive pressure air respirator should be worn.

Store/dispose of residues in accordance with local body regulations.

First Aid

If poisoning occurs, contact a doctor. The Poisons Information Centre may be of assistance – telephone 0800 POISON (NZ), 13-11-26 (Australia).

If swallowed, do NOT induce vomiting. Give a glass of water to drink and get medical attention urgently. If affected by vapour, get into fresh air immediately. If splashed into the eyes, flush them with copious quantities of clean water for 15 minutes and get urgent medical attention.

If splashed onto skin, wash with soap and water.

For further information, refer to the Material Safety Data Sheet for this product.

CAUTION:

Improper use and handling of this product can be hazardous to health.

Do not use this product without first taking all appropriate safety measures to prevent property damage and injuries. These measures may include, without limitation: implementation of proper ventilation, use of proper lamps, wearing of proper protective clothing and masks, tenting and proper separation of application areas. Consult your supervisor. Proper ventilation and protective measures must be provided during application and drying to keep spray mists and vapour concentrations within safe limits and to protect against toxic hazards. Necessary safety equipment must be used and ventilation requirements carefully observed, especially in confined or enclosed spaces, such as tank interiors and buildings.

This product is to be used by those knowledgeable about proper application methods. PPG Industries makes no recommendation about the types of safety measure that may need to be adopted because these depend on application environment and space, of which PPG Industries is unaware and over which it has no control.

If you do not fully understand these warnings and instructions or if you cannot strictly comply with them, do not use the product.

This product is for professional use only. Not for residential use.



269 FAST DRY URETHANE

Substrate Systems

Preparation

Wood – Sand and dust down

MDF – Sand and dust down

Original 2K Urethane – Sand and degrease

Substrate / Recommended System	WFT / DFT (Microns)	Overcoat Time @ 20 Degrees C	Overcoat Preparation
WOOD / MDF (Clear Finish) 1 st coat 700 Urethane Sealer 2 nd coat 269A Clear	95-140 / 20-30 220-270 / 50-60	16-24 hours	Sand 360
WOOD / MDF (Pigmented Finish) 1 st coat 570P 2K Primer White 2 nd coat 269A Colours	70-170 / 30-75 185-220 / 50-60	16-24 hours	Sand 360
ORIGINAL 2K URETHANE FINISH 1 st coat 269A Clear or 269A Colours	220-270 / 50-60 185-220 / 50-60		

WFT = Wet Film Thickness

DFT = Dry Film Thickness

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.

PPG Industries NZ Ltd • 5 Monahan Road • Mt Wellington • Auckland • Phone 0800-263 766 • Fax 0800-659 377
PPG Industries Australia Ltd • McNaughton Rd • Clayton • VIC 3169 • Phone 1300 305 699 • Fax 1300 304 214